

# IDROSTUCCO RS/30

## WATER-BASED BINDER FOR MAKING FILLER

Fast drying water-based filler to be mixed with sawdust to fill parquet gaps and cracks. Idrostucco RS/30 does not shrink and it is odourless. It is easy sandable and has got very low VOC content; completely NMP free.

It can be overcoated also with solvent-based systems.



### Technical data

Chemical-Physical characteristics (20°C - 60% R.H.)			
Appearance	Dense white liquid	Specific gravity	1,00
Viscosity	8000-9000 mPa.s		
Mixing ratios and Times (20°C - 60% R.H.)			
Mixing ratio	Monocomponent	Sanding	40' - 60'
Dust dry	20'	Dilution	water
Technical characteristics			
Indicative coverage	30 m <sup>2</sup> /lt	Application temp.	> 10 °C
Storage and labeling			
Storage (original unopened packaging at amb. temp.)	12 months (Protect from freeze)	Symbols of danger	NONE
Tools cleaning	Just after use clean with water		
Packaging	Canisters of 5 and 10 lt		

### Application

- Sand the wooden floor by coarse and medium grit size sandpaper to obtain a smooth surface, free from grease, oils and waxes.
- Collect sawdust from sanding and prepare a mixture with Idrostucco RS/30 in the proper ratio (indicative dosage: 10 parts of binder with 2 or 3 parts of sawdust) to reach the thickness required: filler must be more or less thick referring to the size of fissures (thinner fissures => more liquid filler).
- Quickly and uniformly spread the filler on the floor using a stainless American spatula taking care to push into the gaps as much product as possible. If necessary repeat the operation.
- After drying (40-60 min) proceed to sand up to 100-120 grit size sandpaper. Before applying any coat carefully check that all the exceeding filler has been removed and clean the surface.

### Notes

- ✓ To obtain the same colour of the wood use the powder obtained from sanding operations.
- ✓ To fill wood holes or big fissures, use the specific two-component polyester filler Nodostuc.

### Norms references

UNI EN 14342:2008 Wood flooring - Characteristics, evaluation of conformity and marking.

### Safety rules

FOR PROFESSIONAL USE ONLY. Strictly respect the information reported on the labels and consult safety data sheets before use.

### Disposing of waste

Dispose not used product and empty containers in accordance of local in force regulations.

**WARNING:** The information reported in present technical data sheet are for guidance only and they do not hold our responsibility. Adapt the use of our products to the environmental conditions and materials to be treated.

REV.2 18-07-2013 Current Technical Data Sheet replaces the previous one.



TOVER S.R.L.  
Via Rosa Luxembourg 2/A  
10093 COLLEGNO (TO)  
P.IVA 07783540011  
R.E.A. n°920259  
Tel.: +39-011/7792823  
Fax: +39-011/7792749  
[www.tover.com](http://www.tover.com)  
e-mail: [info@tover.com](mailto:info@tover.com)  
Made in Italy

