

Veralite® 200 - Technical data sheet

PHYSICAL PROPERTIES			
Properties	Method	Units	Veralite [□] 200
Specific gravity	ISO 1183	g/cm ³	1,27
Water absorption	ISO 62	%	0,15
MECHANICAL PROPERTIES			
Properties	Method	Units	Veralite [□] 200
Tensile strength	ISO 527	MPa	51,5
Elongation at break	ISO 527	%	> 100
Tensile modulus	ISO 527	MPa	± 2200
Impact strength unnotched	ISO 180	KJ/m ²	no burst
Impact strength notched	ISO 180	KJ/m ²	9,0
Rockwell hardness	DIN 2039	M / R	M85 / R115
THERMAL PROPERTIES			
Properties	Method	Units	Veralite [□] 200
Coefficient of linear expansion	ASTMD696	mm/mC°	± 0,060
Specific Heat	DSC	J/gC°	1,13
Heat deflection temp. (0,45 MPa)	ISO 75	°C	72
Heat deflection temp. (1,82 MPa)	ISO 75	°C	68
Vicat softening point (1 kg)	ISO 306	°C	82
Vicat softening point (5 kg)	ISO 306	°C	78
O'PTICAL PROPERTIES			
Properties	Method	Units	Veralite [□] 200
Light transmission	ASTMD1003	%	86 - 90*
Haze	ASTMD1003	%	< 1

Gloss (60° angle)	ASTMD1003	units	159
-------------------	-----------	-------	-----

Veralite[®] 200 - Technical data sheet

ELECTRICAL PROPERTIES

Properties	Method	Units	Veralite [®] 200
Surface resistivity	ASTMD257	Ω	1*E15
Dielectric constant (1 MHz)	ASTMD150	~	2,4
Dissipation factor (tgδ , 1 MHz)	ASTMD150	~	0,020
Dielectric strength (500V/sec)	ASTMD149	kV/mm	16
Glow wire test	IEC 695/2.1	C°	650

BARRIER PROPERTIES

Properties	Method	Units	Veralite [®] 200
Permeability for water vapour	ASTMF372	g/mm/m ² /24h	1,5
Gas permeability for CO ₂	ASTMD1434	g/mm/m ² /24h	49
Gas permeability for O ₂	ASTMD3985	g/mm/m ² /24h	10

Temporary and limited list made to our best knowledge at this time - based upon 3 mm sheet.

The technical data concerning our products are not binding and are given for guidance only. *

Test results from 1 - 3 mm