Technical Data Sheet



Product name: AquaSolve™ - PVA

Version: v3

AquaSolve is a high-end cold water soluble PVA (PolyVinyl Alcohol) type of 3D printer filament, which bonds very well to a variety of (thermo)plastics – such as PLA, PETG, ABS, and more – that print within a similar temperature range. This makes AquaSolve an excellent PVA support material for dual extrusion prints.

AquaSolve™ PVA has a limited smell during printing and is non-toxic and biodegradable once dissolved in water.

Properties	Typical value	Test Method	Test condition	
Physical				
Specific gravity	1.23 g/cc	ASTM D1505	-	
Melt flow rate	14-20 g/10min	-	190° C/21.6Kg	
Water absorption	-	-	-	
Moisture absorption	-	-		
Mechanical				
Impact strength	1.6 KJ/m²	ISO 179	Charpy Notched @23° C (73° F)	
Tensile strength	78 Mpa	ISO 527	Stress @ Yield 23° C	
Tensile modulus	3860 Mpa	ISO 527	-	
Elongation at break	9.90%	ISO 527	Nominal Strain at Break, 23° C	
Flexural strength	-	-	<u>-</u>	
Flexural modulus	-	-	-	
Hardness	-	-	-	
Thermal				
Print temperature	± 180 - 205° C	-	-	
Melting termperature	± 163	-	-	
Viscat softening temp.	± 60.2° C	ISO 306	VST/A/50 (50° C/h, 10N)	
Optical				
Haze	-	-	-	
Transmittance	-	-	-	
Gloss	-	-	-	

Product details, ce	rtifications and com	pliance	Diameter	Tolerance	Roundness
HS Code	39169090		1.75mm	± 0.05mm	≥ 95%
REACH compliant	Yes		2.85mm	± 0.10mm	≥ 95%
RoHS certified	Yes				
Formfutura BV	CoC:	69099502		Tel:	+31 (0)85 002 0881
Groenestraat 215	VAT:	NL857733709B01		Email:	info@formfutura.com
6531 HH Nijmegen	EORI:	NL857733709		Website:	www.formfutura.com
The Netherlands					

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.