

FORMFUTURA PLATINUM LCD SERIES

First / Burn-In Layer Curing Times 50 microns

Solid Resins: 4 layers at 100 Microns 120 to 150 seconds of curing
Translucent Resins: 4 layers at 50 Microns 75 to 90 seconds of curing

Base / Normal layers Curing Times at 50 microns

Translucent Black: 12sec
Translucent Aquamarine: 10sec
Translucent Blue: 12sec
Translucent Red: 11sec

Solid White: 13.5sec
Solid Black: 11sec
Solid Light Grey: 12sec

First / Burn-In Layer Curing Times 100 microns

Solid Resins: 4 layers at 100 Microns 120 to 150 seconds of curing

Base / Normal layers Curing Times at 100 microns

Solid White: 15.5sec
Solid Black: 17sec
Solid Light Grey: 15sec