

TECHNICAL DATA SHEET

Premium PLA

Date of issue: 16-1-2020

Date of update: 23-8-2024

Product specifications

Premium PLA is a more pure PLA type of 3D printer filament with higher crystallinity, which makes it the PLA of choice for 3D printing parts with overhangs and for objects where bridging is required.

Important key features

Warp-free printing and no deformation after cooling
Improved flowing behaviour and inter-layer adhesion
Biodegradable

Suitable applications

Detailed prints with overhang or bridge
Automotive
Aviation

Recommended pretreatment

Drying

Not necessary
50 - 40 °C
6 h

Print with

Enclosure No
Dry box No

Recommended print settings regular speed

Print speed 25 - 150 mm/s
Nozzle temperature 185 - 210 °C
Bed temperature 50 - 60 °C
Fan speed 80 - 100 %

Recommended print settings high speed

Premium PLA is high speed compatible. Our recommended settings will be added once available. Please take note that the nozzle temperature and fan speed need to be raised when printing at high speed.

Material properties	Typical value	Unit of Measure	Test method	Test condition
Density				
Specific gravity	1,24	g/cm ³	ASTM D792	
Melt flow rate	6	g/10min	ASTM D1238	210°C/2,16kg

Mechanical properties

Impact strenght	16	J/m	ASTM D256	Izod notched 23°C
Tensile strenght at yield	60	MPa	ASTM D882	
Tensile strenght at break	53	MPa	ASTM D882	
Tensile modulus	3,5	GPa	ASTM D882	
Elongation at yield	6	%	ASTM D882	
Elongation at break				
Flexural strenght	83	MPa	ASTM D790	
Flexural modulus	3,8	MPa	ASTM D790	
Rockwell hardness				

Thermal properties

Melting temperature				
Heat deflection temperature	55	°C	ASTM E2092	HDT A
Vicat softening temperature				
Glass transition temperature	60	°C	ASTM D3418	

Product export information

HS code	Description	Origin
39169090	Monofilament for 3D printing	European Union

Disclaimer

The product- and technical data provided in this datasheet is correct to the best of FormFutura BV's knowledge and are intended for reference and comparison purposes only. Actual values may vary according to printing conditions, model complexity, environmental conditions, etcetera. Typical values are indicative only and are not to be construed as being binding specifications. All other information supplied, including that herein, is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine a product's suitability for a particular purpose. We make no warranty, express or implied, including regarding any information supplied or the data upon which it is based or the results to be obtained from the use of such products or information, or concerning product, whether of satisfactory quality, merchantability, fitness for any particular purpose or otherwise, or with respect to intellectual property infringement as a result of use of information or products, and none shall be implied.

