

## Product name: Tough PLA

FormFutura Tough PLA is a 3D printer filament that is roughly 750% more impact resistant than regular PLA filaments.

Our Tough PLA filament is a performance PLA that combines durability with ABS-like strength properties and yet it is a significantly stiffer 3D printing material than ABS filaments. Tough PLA exhibits excellent layer adhesion allowing 3D printed objects to achieve similar mechanical strength properties compared to injection molding.

Properties	Typical value	Test Method	Test condition
<b>Physical</b>			
Specific gravity	1.21 g/cc	ISO 1183	-
Melt flow rate	8.75 g/10min	ISO 1133	210° C/2.16Kg
Water absorption	-	-	-
Moisture absorption	-	-	-
<b>Mechanical</b>			
Impact strength	29.8 KJ/m <sup>2</sup>	ISO 179	Charpy Notched @23° C (73° F)
Tensile strength	46 Mpa	ISO 527	@ yield
Tensile modulus	2750 Mpa	ISO 527	-
Elongation at break	-	-	-
Flexural strength	-	-	-
Flexural modulus	-	-	-
Hardness	-	-	-
<b>Thermal</b>			
Print temperature	± 2150 - 225° C	-	-
Melting temperature	-	-	-
Viscat softening temp.	± 57° C	ISO 306	-
<b>Optical</b>			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance		Diameter	Tolerance	Roundness
HS Code	39169090	1.75mm	± 0.05mm	≥ 95%
REACH compliant	Yes	2.85mm	± 0.10mm	≥ 95%
RoHS certified	Yes			

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.