

ULTEM™ FILAMENT AM1010F

DESCRIPTION

ULTEM™ AM1010F filament is a polyetherimide product for 3D printing applications manufactured from ULTEM™ 1010 resin. The filament provides high heat resistance and mechanical strength, is UL94 V-0 compliant at 1.5 mm and 5VA compliant at 3.0 mm.

TYPICAL PROPERTY VALUES

Revision 20210812

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Modulus			
XY ORIENTATION	2750	MPa	ASTM D638
XZ ORIENTATION	2865	MPa	ASTM D638
ZX ORIENTATION	2840	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min			
XY ORIENTATION	73	MPa	ASTM D638
XZ ORIENTATION	80	MPa	ASTM D638
ZX ORIENTATION	34	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min			
XY ORIENTATION	4.0	%	ASTM D638
XZ ORIENTATION	3.8	%	ASTM D638
ZX ORIENTATION	1.3	%	ASTM D638
Flexural Modulus, 1.3 mm/min			
XY ORIENTATION	2520	MPa	ASTM D790
XZ ORIENTATION	2840	MPa	ASTM D790
ZX ORIENTATION	2380	MPa	ASTM D790
Izod Impact, notched, 23°C			
XY ORIENTATION	31	J/m	ASTM D256
XZ ORIENTATION	37	J/m	ASTM D256
ZX ORIENTATION	30	J/m	ASTM D256
Izod Impact, un-notched, 23°C			
XY ORIENTATION	273	J/m	ASTM D256
XZ ORIENTATION	240	J/m	ASTM D256
ZX ORIENTATION	128	J/m	ASTM D256
THERMAL			
HDT, 1.82 MPa, 3.2 mm, unannealed			
XY ORIENTATION	211	°C	ASTM D648
XZ ORIENTATION	210	°C	ASTM D648
ZX ORIENTATION	208	°C	ASTM D648
Coefficient of Thermal Expansion - flow			
XY ORIENTATION	51	µm/(m·°C)	ASTM E831
XZ ORIENTATION	53	µm/(m·°C)	ASTM E831
ZX ORIENTATION	53	µm/(m·°C)	ASTM E831
Coefficient of Thermal Expansion - x-flow			
XY ORIENTATION	53	µm/(m·°C)	ASTM E831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
XZ ORIENTATION	52	$\mu\text{m}/(\text{m}^\circ\text{C})$	ASTM E831
ZX ORIENTATION	53	$\mu\text{m}/(\text{m}^\circ\text{C})$	ASTM E831
PHYSICAL			
Density	1.275	g/cm^3	ASTM D792
ELECTRICAL			
Volume Resistivity			
XY ORIENTATION	6.24E+14	Ohm-cm	ASTM D257
XZ ORIENTATION	1.26E+15	Ohm-cm	ASTM D257
FLAME CHARACTERISTICS			
FAA Flammability			
XY ORIENTATION, 1.5mm	Passed	-	FAR 25.853
OSU total heat release (2 minute test)			
XY ORIENTATION, 1.5mm	5	$\text{kW}\cdot\text{min}/\text{m}^2$	FAR 25.853
OSU peak heat release rate (5 minute test)			
XY ORIENTATION, 1.5mm	23	kW/m^2	FAR 25.853
Vertical Burn (60s) passes at			
XY ORIENTATION, 1.5mm	2	Seconds	FAR 25.853
Vertical Burn (12s) passes at			
XY ORIENTATION, 1.5mm	0	Seconds	FAR 25.853
UL94 Flame Class Rating ⁽¹⁾			
XY ORIENTATION, 1.5mm	VO	-	UL 94
XZ ORIENTATION, 1.5mm	VO	-	UL 94
ZX ORIENTATION, 1.5mm	VO	-	UL 94
XY ORIENTATION, 3.0mm	5VA	-	UL 94
THERMAL PROPERTIES			
Vicat Softening Temperature			
XY ORIENTATION, Rate B/50	220	$^\circ\text{C}$	ASTM D1525
XZ ORIENTATION, Rate B/50	220	$^\circ\text{C}$	ASTM D1525
ZX ORIENTATION, Rate B/50	220	$^\circ\text{C}$	ASTM D1525
ELECTRICAL PROPERTIES			
Dielectric Constant			
XY ORIENTATION at 1.9 GHz	2.9	-	ASTM D150
XZ ORIENTATION at 1.9 GHz	2.9	-	ASTM D150
Dissipation Factor			
XY ORIENTATION at 1.9 GHz	0.003	-	ASTM D150
XZ ORIENTATION, 1.9 GHz	0.003	-	ASTM D150

(1) UL results provided herein may not be sufficient to waive end use part testing for UL listing. Contact UL for further details.

DISCLAIMER

Typical values only. Not intended for design or specification purposes. Variations within normal tolerances are possible for various colors. Test coupons were printed using a Stratasys FORTUS† 900mc printer under standard parameters unless otherwise noted.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.