

## TECHNICAL DATA

### COBALT OCTOATE 10%

**Product Description:** Cobalt bearing oxidative paint dryer in distilled light petroleum solvent

#### Physical and Chemical Properties

	<i>Limits</i>	<i>Method*</i>	<i>Reference</i>
<b>Appearance</b>	<i>Clear Liquid</i>	<i>ETY 030</i>	<i>ASTM D564</i>
<b>Co Metal (%)</b>	<i>9.80-10.20</i>	<i>ETY 053</i>	<i>ASTM D2373</i>
<b>Colour</b>	<i>Dark Blue</i>	<i>ETY 051</i>	<i>ASTM D564</i>
<b>Total solid (% , 105°C 3 hours)</b>	<i>Max. 75</i>	<i>ETY 007/11</i>	<i>ASTM D564</i>
<b>Density (gr/cm<sup>3</sup> , 25 °C)</b>	<i>0.950-1.017</i>	<i>ETY 003/4</i>	

\* Test methods are available upon request.

---

**Applications:** Primary paint dryer

---

**Standard Packaging:** In steel drums or plastic containers

---

**Storage Conditions:** Should be stored in well-ventilated conditions and kept away from flame and peroxides. The cover of drum should be closed tightly.

---

**Shelf life:** 1 year from production date.

---

V\_03\_2021